

Technical Data Sheet (Lumber)



Product code XF30-65/100-6FT-PSS XL20-205/625-6FT-UAC XL40-152/625-6FT-UAC

Size L1860*W65/100*T30 L1860*W205/625*T20 L1860*W152/625*T40

Product Description

dassoXTR Lumber is solid and high density board, made from compressed bamboo fibers with a special, patented heat treatment process, making it one of the strongest, hardest and most durable materials on the market to create the perfect space for outdoor entertainment and relaxation. Like any untreated tropical hardwood species, when exposed to outdoor conditions, dassoXTR Lumber will turn grey over time creating a very natural look.

Product Technical Specification

Tolerance ±0.5 ±0.15 ±0.15 Physical Properties Standard Intervention Intervention Physical Properties Standard Intervention Intervention Physical Properties Intervention Intervention Intervention	Specifications Properties	Length/mm	Width/mm	Thickness/mm	
Density/Specific Gravity1.15 g/cm3Moisture content10%-14%Hardness106.8N/mm²(DIN EN 1534)Static Bending StrengthMean value:74.4N/mm² (DIN EN 408)Modulus of ElasticityMean value:19100N/mm² (DIN EN 408)	Tolerance	±0.5	±0.15	±0.15	
Moisture content10%-14%Hardness106.8N/mm²(DIN EN 1534)Static Bending StrengthMean value:74.4N/mm² (DIN EN 408)Modulus of ElasticityMean value:19100N/mm² (DIN EN 408)	Physical Properties		Standard		
Hardness106.8N/mm²(DIN EN 1534)Static Bending StrengthMean value:74.4N/mm² (DIN EN 408)Modulus of ElasticityMean value:19100N/mm² (DIN EN 408)	Density/Specific Gravity		1.15 g/cm3	1.15 g/cm3	
Static Bending StrengthMean value:74.4N/mm² (DIN EN 408)Modulus of ElasticityMean value:19100N/mm² (DIN EN 408)	Moisture content		10%-14%	10%-14%	
Modulus of Elasticity Mean value:19100N/mm² (DIN EN 408)	Hardness		106.8N/mm²(DIN EN 1	106.8N/mm²(DIN EN 1534)	
	Static Bending Strength		Mean value:74.4N/mm	Mean value:74.4N/mm ² (DIN EN 408)	
Thickness of Swelling Rate4.6% (DIN EN 15534-1)	Modulus of Elasticity		Mean value:19100N/m	Mean value:19100N/mm ² (DIN EN 408)	
	Thickness of Swelling Rate		4.6% (DIN EN 15534-1)	4.6% (DIN EN 15534-1)	

www.dassogroup.com

o [°] dasso	dassoXTR dassoCTECH for Exterior Use
Width of Swelling Rate	0.6% (DIN EN 15534-1)
Water absorption rate	4.2% (DIN EN 15534-1)
Warping	≤ 6mm and quantity is less than 10%.
Banana Shape	≤ 1mm/m along the length of the panels
Bamboo Nodes	Nodes are separated its width ≤ 10 mm.
Height Difference	≤ 0.5mm
Packaging and label	According to packaging layout drawing, check the label

Biological and chemical Properties	Standard
Termite Resistance Level	DC M (EN117)
Biological Durability	DC 1 (EN 350:2016)
Release of Formaldehyde	E1(<0.1mg/L) (GB/T17657-2013)

Storage

- The warehouse should be well ventilated, with relative humidity from 45% to 75% at temperatures ranging from 50°F (+10°C) to 104°F (+40°C).
- Do not store product in pest infested and/or unsuitable warehouse.
- Leave the products in its original package when not in use, cover the bundles from top and bottom to avoid the influence of climatic events and other environmental hazards.
- Store the product horizontally on the ground with pallet shoe on every pallet. The bottom pallet should be placed on an even footing on spacer-pads or palettes. The maximum height of stacked bundles should not exceed 4.5 m.
- The difference between the spacers should not be more than 600mm, with distance of starting and ending spacer from the edge of the bundle not exceeding 200mm (the number of spacers should not be less than 3).